

Technical Datasheet

Hannoband[®]-HBD

Product description

Joint sealing tape of polyurethane soft foam with acrylate dispersion impregnation.

Product properties

- Heavy rain tightness (EN 1027) ≥ 300 Pa (corresponds with the BG 2 requirements for heavy rain tightness in DIN 18542:2009)
- Values ≤ 600 Pa possible, depending on the compression and joint width
- 5 year function guarantee



Areas of application

Window construction

- Heavy rain tight connection joints
- Thermal sealing between the window frame and the masonry, profile coupling, backfilling, strips.

Facade technology

- Support for in-situ concrete/concrete element
- Boarding connection when concreting

Interior work

- Light partitions
- Decoupling of double floors

High-pitched/flat roof

- Roof area window
- Pantile sealing
- Ridge/groin/groove/dormer window

Instructions for use

Please adhere to the instructions for use which are enclosed in each of the boxes.

Form of delivery

Colour: grey, black

Pre-compressed on rolls, self-adhesive from one side (roll lengths: depending on the density, widths: from 10 mm).

Cleaning

The skin can be cleaned with soap and water. The impregnate and/or residue adhesive can be removed with a petroleum-based cleaning agent. Please observe the safety regulations.

Technical Datasheet

Safety instructions

On the basis of existing data and experience, the product is not hazardous material in the meaning of the Hazardous Material Regulations and the corresponding EC directives. We recommend however that you take the same care and use the same hygiene as with chemical materials.

Technical Data

Fire behaviour	DIN 4102, T1	B2 at 50% compression; P-NDS04-283, MPA*
Temperature resistant		between -30° C and 100° C, max. 130° C briefly
Joint permeability	DIN EN 1026	$a_n \leq 1,0$
Heavy rain tightness	DIN EN 1027	≥ 300 Pa
Tensile strength	DIN EN ISO 1798	> 60 kPa
Elongation at break	DIN EN ISO 1798	$> 180\%$
Compressive strain deformation properties	DIN EN ISO 3386	ca. 2,3 kPa
Weathering resistance	Freibewitterung	> 15 years; 2009.1115, MPA2*
Storage stability		ca. 18 months from the date of production

*MPA: Material Testing Agency for the Construction Industry, Hanover; MPA2: MPA-Hanover, Material testing laboratory

Disposal

Residue tape can be disposed of in the household waste. The local regulations are to be adhered to.

Restriction of liability

Our General Terms and Conditions of Sales with the warranty conditions which you can refer to at www.hanno.com, have validity. This data sheet provides non-binding information without the assumption of a guarantee. The stipulated instructions for use are to be adapted to the given conditions. The user is obligated to validating the suitability and application possibility of the product by testing it himself, so as to avoid failures for which we assume no liability. The right to make technical changes are reserved. You will find the latest version of this datasheet under www.hanno.com.