Technical Data Sheet

Hanno®-Foam HW 30 TS

Product description

Sealing foam on a polyether basis, with a high proportion of closed cells.

Product characteristics

Low-emission, hydrolytically stable, halogen-free, self-extinguishing

Areas of Application

suitable for the creation of soft-elastic seals, e.g. for

- ventilation systems
- door panels
- lighting fixtures
- condensing boiler


Lieferform

Blocks, slabs, blanks, stampings (dimensions upon request), rolls.

Special Instructions

Materials with a soft foam structure tend to be subjected to dimensional changes when being processed (punching, cutting, pressing, wrapping, inserting, etc.). Generally speaking, the dimension tolerances of DIN 7715-P3 can be adhered to. Please contact our customer service if you have special demands concerning the dimensional accuracy.

Hanno®-Foam HW 30 TS is a development product for which no complete tests are available. The technical information is based on the manufacturer's information and internal tests. Availability is subject to technical testing and feasibility for the respective desired dimensions. Technical changes in the course of further development work are possible.



Use

Hanno®-Foam HW 30 TS can be rendered self-adhesive, is easy to punch and cut.

Cleaning

No significant soiling by the material is to be expected. Clean skin with soap and water. Adhesive residue can be removed with petroleum-based cleaning agent. Observe safety instructions.

Disposal

Hanno[®]-Foam HW 30 TS can be disposed of with the household waste. Observe local regulations.

Safety Instructions

On the basis of existing data and experience, the product is not hazardous material in the sense of the hazardous materials regulations and the corresponding EC directives. However, we recommend that you take the same care and use the same hygiene as with chemical materials.

Technical Data

Color	<u>-</u>	anthracite
Specific Weight	EN ISO 845	approx. 33kg/m³
Compression hardness	EN ISO 3386	approx. 5 kPa (40 %)
Tensile strength	EN ISO 1798	> 70 kPa
Elongation at break	EN ISO 1798	> 90%
Burning rate	FMVSS302 DIN 75200	< 100 mm/min

Hanno Werk GmbH & Co. KG

Hanno-Ring 3–5 30880 Laatzen Germany

Tel: +49 5102 7000-0 info@hanno.com





Hanno®-Foam HW 30 TS

Limitation of liability

Our general terms and conditions of sale with warranty conditions, which you can refer to at www.hanno.com, apply. This datasheet provides non-binding information without guarantee. The stipulated instructions for use are to be adapted to the respective conditions. The user is obligated to check the suitability and applicability through their own testing in order to avoid failures for which we assume no liability. Subject to technical changes.

You can request the latest version of this datasheet at info@hanno.com.

Hanno-Ring 3-5 30880 Laatzen Germany Telefon: +49 5102 7000-0 info@hanno.com www.hanno.com



