



## Product description

Mainly open-cell polyurethane foam on a polyether basis

## Product properties

excellent elasticity behaviour with a good padding and restoring capacity, good hydrolysis resistance, moderate UV-resistance, insensitive to petrol vapours and mineral oil splashes

## Applications

- Automotive
- Mechanical engineering and apparatus engineering industries.

## Form of Delivery

Blocks, slabs, blanks, stampings (dimensions upon request)

## Processing

Hanno® Foam HW 30 sfl can be rendered self-adhesive, is easy to punch and cut

## Special Instructions

Materials with a soft foam structure tend to be subjected to dimensional changes when being processed (punching, cutting, pressing, wrapping, inserting, etc.). Generally speaking, the dimension tolerances of DIN 7715-P3 can be adhered to. Please contact our customer service if you have special demands concerning the dimensional accuracy.

## Cleaning

No significant soiling by the material is to be expected. When using self-adhesive components, residue adhesive can be removed with a petroleum-based cleaning agent, if necessary. Please observe the safety regulations for the used cleaning agent.

## Environment and disposal

Hanno® Foam can be disposed of as residential waste according to local disposal regulations.

## Safety Instructions

Based on available data and experience, the product is not a hazardous substance as defined by the Hazardous Substances Regulation and corresponding EU directives. We recommend however that you take the same care and use the same hygiene as is customary with working materials.

## Restriction of liability

Our General Terms and Conditions of Sales with the warranty conditions which you can refer to at **www.hanno.com**, apply. This data sheet provides non-binding information without the assurance of guarantee.

## Technical data

Colour	–	grey
Specific gravity	DIN EN ISO 845	25.5 ± 1 kg/m³
Compression hardness	DIN EN ISO 3386	3.3 ± 0,5 kPa (40%)
Tensile strength	DIN EN ISO 1798	>100 kPa
Elongation at break	DIN EN ISO 1798	>200%
Compression set	DIN EN ISO 1856	≤ 4%
Operative temperature range	–	-40 to +100°C (short-time higher)
Behaviour on fire	FMVSS 302/ DIN 75200	<100 mm/min

Hanno Werk GmbH & Co. KG

Hanno-Ring 3–5  
30880 Laatzen  
Germany  
Tel: +49 5102 7000-0  
info@hanno.com  
www.hanno.com



# Hanno®-Foam HW 30 sfl

The stipulated instructions for use are to be adapted to the given conditions. The user is obligated to validating the suitability and application possibility of the product by testing it himself, so as to avoid failures for which we assume no liability. The right to make technical changes is reserved.

You can request the latest version of this datasheet from **info@hanno.com**.

Hanno Werk GmbH & Co. KG

Hanno-Ring 3-5  
30880 Laatzen  
Germany

Tel: +49 5102 7000-0  
info@hanno.com  
www.hanno.com

